



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09D 9/00	A2	(11) International Publication Number: WO 94/22965 (43) International Publication Date: 13 October 1994 (13.10.94)
(21) International Application Number: PCT/US94/01537 (22) International Filing Date: 10 February 1994 (10.02.94) (30) Priority Data: 08/040,368 30 March 1993 (30.03.93) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventors: KORELTZ, Francis, J.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). McDONELL, James, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). ONWUMERE, Fidelis, C.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). FUNABIKI, Toshihiro; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: WENDT, Jeffrey, L. et al.; Office of Intellectual Property Counsel, Minnesota Mining and Manufacturing Company, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).		(81) Designated States: BR, CA, CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: IMPROVED FLOOR STRIPPING COMPOSITION AND METHOD (57) Abstract The present invention is drawn toward compositions and methods of using same, the compositions comprising (in diluted form): a) an effective amount of a phenyl substituted alkyl alcohol having a water solubility of at least 0.1 weight percent (preferably benzyl alcohol); b) a coupler; and c) water, wherein the amount of the coupler is at least 3.0 times the amount necessary to completely solubilize the phenyl substituted alkyl alcohol in the water. Preferred couplers are the salt of a monofunctional water-soluble amine and an organic acid comprising at least one water-insoluble organic acid having from 6-10 carbon atoms. Methods of removing coatings such as standard urethane/acrylic sealer finishes from floors using the inventive compositions are also described.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

IMPROVED FLOOR STRIPPING COMPOSITION AND METHOD

5 The present invention is drawn toward compositions and methods of using compositions to strip (i.e. remove) coatings such as standard floor finishes and/or greasy residues from hard surfaces such as floors.

10 Various concentrated and ready-to-use compositions are available for stripping floor finishes and/or greasy residues from surfaces such as floors, counter tops, and other surfaces. U.S. Patent No. 5,080,831 describes aqueous cleaner/degreaser compositions comprising an organic solvent, a solubilizing additive consisting of a
15 surfactant and a coupler and balance water. Organic solvents claimed as being useful in the '831 patent are described as being sparingly water-soluble, having a water solubility ranging from approximately 0.2 to approximately 6 weight percent in water, such as benzyl
20 alcohol. Compositions within the '831 patent claims include a solubilizing additive present in an amount not exceeding approximately twofold that required to completely solubilize the organic solvent. Among other criteria, the organic solvent cannot be a hydrocarbon.
25 U.S. Pat. No. 5,158,710 of the same assignee as the '831 patent describes similar compositions, some of the compositions useful as floor strippers.

 U.S. Patent No. 4,414,128 describes liquid detergent compositions which comprise a terpene (a hydrocarbon), a
30 surfactant, a polar solvent such as benzyl alcohol, and water. Terpenes described as being useful in these compositions include hydrocarbon terpenes and terpene alcohols.

 In light of the above-described compositions, one
35 would expect that compositions comprising sparingly water-soluble organic solvents and a coupler, with the coupler concentration substantially above twofold times that necessary to completely solubilize the organic

solvent would not be effective in removing floor finishes and the like from surfaces, especially in the presence of a hydrocarbon.

Contrary to the teachings of the art, the inventors
5 herein have discovered that compositions containing at least one of a select class of slightly water-soluble organic solvents and a coupler, wherein the coupler is present at greater than 2.0 times that required to completely solubilize the solvent, are surprisingly
10 extremely efficient in removing standard floor finishes from various hard surfaces. In particular, the compositions of the present invention show a remarkable ability to remove multiple coatings of a standard floor coating comprising a urethane polymer-based sealer and an
15 acrylic polymer-based finish from floors and/or base boards. Compositions within the invention have also found use in removing ink from hard surfaces.

In accordance with the present invention, the inventors herein have surprisingly discovered that
20 compositions suitable for stripping coatings (i.e., removing at least a portion of the coating) from a surface, preferably after being diluted with water, especially greasy residues and floor finishes from floors such as vinyl tile floors, terrazzo, marble, and the
25 like, may be formulated characterized by:

- a) an effective amount of a phenyl substituted alkyl alcohol having a water solubility of at least 0.1 weight percent (preferably benzyl alcohol); and
- 30 b) a coupler,

wherein the amount of the coupler is present in an amount which is at least 3.0 times the amount necessary to completely solubilize the phenyl substituted alkyl
35 alcohol.

"Diluted with water" as used herein means the inventive compositions are reduced in actives

concentration by adding from 0.1 part to 30 parts water per part of inventive composition. Specific dilution ratios are dependent on the end use, and examples are given herein below.

5 "Effective amount" when referring to the phenyl substituted alkyl alcohol means that it is present in an amount which removes at least 10 percent of a standard urethane/acrylic floor sealer/finish from a composition vinyl tile within 2.5 minutes, in accordance with a
10 standard test (see Test Methods section).

As used herein the term "coupler" refers to a compound or a physical or chemical combination of compounds having the capability of increasing the phase-stability of the compositions of the invention. Couplers
15 typically and preferably comprise low molecular weight (molecular weights less than about 500) organic compounds. The term "hydrotrope" is also frequently used interchangeably with coupler. One preferred coupler for use in the invention is the reaction product of
20 monoethanolamine with an organic acid comprising n-octanoic acid and n-decanoic acid.

Preferred compositions also include an effective amount of a surfactant and an effective amount of a chelating agent. Typically the surfactant, preferably a
25 low-foaming fluorochemical surfactant, is present at a weight ratio of surfactant to phenyl substituted alkyl alcohol of about 0.005:1. Chelating agents may be preferred when the compositions are to be stored in containers and then dispensed after prolonged storage to
30 avoid precipitation of coupler. Preferred chelating agents include 1-hydroxyethylidene-1,1-diphosphonic acid, and the like, present at a weight ratio of chelating agent to phenyl substituted alkyl alcohol ranging from about 0.005:1 to about 0.015:1.

35 The compositions of the invention are substantially more effective in removing multiple coatings of a standard floor sealer/finish comprising urethane/acrylic

polymers than the previously described patented compositions, as shown in the Examples.

It has also been discovered that compositions of the invention further containing a terpene, such as d-
5 limonene, although less effective than compositions of the invention devoid of a hydrocarbon terpene, remove a standard floor sealer/finish comprising urethane/acrylic polymers more effectively than the earlier discussed patented compositions. The presence of the terpene also
10 serves to dissolve hydrophobic materials typically deposited on these coatings, and affords pleasant odor.

Another aspect of the invention is a method of removing a sealer/finish coating from a surface, the method comprising:

- 15 a) applying to the coating a composition within the invention; and
- b) allowing the composition to contact the coating for a time sufficient to at least partially remove the coating. As used herein "coating" is meant to include a
20 single layer or multiple layers of the same composition, and coatings comprising two or more layers, each layer comprising dissimilar compositions.

Preferred methods comprise abrading the coating after a predetermined contact time between the coating
25 and the composition, such as with a lofty, open, three dimensional nonwoven pad, such as those described in U.S. Pat. No. 2,958,593, which is attached to a conventional floor maintenance machine. Alternatively, the composition may be applied and removed using a natural or
30 synthetic fiber-based cloth, such as a cotton or synthetic cloth.

The compositions of the present invention are especially useful in stripping urethane sealants, acrylic floor finishes, and urethane/acrylic "sealer/ finishes"
35 from flooring materials such as composition vinyl tiles, marble, terrazzo, and the like. The compositions of the invention may also be employed in stripping grease, oil,

and the like, from similar surfaces such as floors in restaurants, homes, automobile repair facilities, and the like. The various ingredients of the compositions of the invention will now be discussed in more detail.

5 **Phenyl Substituted Alkyl Alcohols**

Phenyl substituted alkyl alcohols function as the coating dissolving and/or grease solubilizing component of the compositions of the invention. Phenyl substituted alkyl alcohols useful in the present invention have a
10 water solubility of at least about 0.1 weight percent, more preferably ranging from about 0.2 to about 6 percent by weight in water at 20°C. Organic solvents having a water solubility ranging from about 0.2 to about 6 weight percent are commonly referred to in the art as
15 "sparingly" or "slightly" water-soluble organic solvents.

Phenyl substituted alkyl alcohols useful in the invention include benzyl alcohol, alpha-phenylethyl alcohol, beta-phenylethyl alcohol, ethylene glycol benzyl ether, and the like. One particularly preferred phenyl
20 substituted alkyl alcohol which is slightly water-soluble is benzyl alcohol, due to its solvent properties, relatively low toxicity, availability, and because it is relatively nonhazardous to transport. It also has not unpleasant odor.

25 Phenyl substituted alkyl alcohols in which the phenyl group is also substituted, for example with C₁ - C₄ alkyl groups, may be useful in the invention, provided they have the requisite water-solubility.

In addition to the water solubility criteria
30 mentioned above, and as previously mentioned, it is also desirable but not essential that the phenyl substituted alkyl alcohols useful in the invention have a relatively low volatility or high flash point (in excess of 60°C), exhibit a low level of odor, be chemically stable,
35 nontoxic, nonhazardous and commercially available.

The phenyl substituted alkyl alcohol is preferably present in the composition in an amount sufficient to

remove the coating to which it is applied, the amount varying with the coating or residue to be removed. Compositions within the invention preferably have the following weight ratios of active ingredients:

- 5 Phenyl substituted alkyl alcohol to coupler, from 1:2 to 1:1, preferably 4:6;
 Phenyl substituted alkyl alcohol to surfactant, about 0.005:1;
 Phenyl substituted alkyl alcohol to chelating agent,
10 from about 0.005:1 to about 0.02:1.

- For particularly heavy greasy residues or old, multiple surface coatings, the weight percentage of phenyl substituted alkyl alcohol in the ready-to-use composition may be as high as 10 weight percent. If a
15 less aggressive composition is desired, one may dilute the concentrates so that the weight percentage of phenyl substituted alkyl alcohol is as low as 1.0 weight percent. A preferred ready-to-use composition includes from about 2.5 to about 4.5 wt% alcohol. These
20 concentrations of alcohol may be obtained by diluting the concentrates listed in Table A with from 8 to 15 parts by weight water as in the Examples. When the concentrates mentioned in Table A are diluted to about 1 part concentrate to 4 parts water, the diluted version may
25 find use as a sprayable cleaner. Trigger-spray devices are known in the art and not considered a part of this invention. The 1:4 diluted compositions of the invention may also be formulated as an aerosol. The concentrates of Table A may be used as an ink remover, or remover of
30 similar compositions.

TABLE A

	<u>Ingredient</u>	<u>Concentrate 1</u>	<u>Concentrate 2</u>
5	Benzyl alcohol	39.9	37.9
	MEA	33.9	33.9
10	n-octanoic acid	25.0	25.0
	FC-135	0.20	0.20
15	dye	0.50	0.50
	chelating agent	0.50	0.50
	d-limonene	---	2.00
20			

When the weight percentage of phenyl substituted alkyl alcohol is less than about 1 weight percent, compositions within the invention may not have the requisite cleaning power to remove greasy residues or surface finishes in user acceptable times. When the concentration of the phenyl substituted alkyl alcohol is over about 10 weight percent in ready-to-use compositions, there does not appear to be any beneficial effect over that observed for 10 weight percent compositions, except when used, for example, as an ink remover. When used as an ink remover, the concentration of phenyl substituted alkyl alcohol may be as high as 40 weight percent.

35 **Couplers**

Couplers function to increase the phase stability of the composition by increasing the apparent water solubility of the alcohol. Suitable couplers for use in the compositions of the present invention include the salt of a low molecular weight monofunctional amine and a low molecular weight organic acid. Couplers of this nature allow higher concentration of the phenyl substituted alkyl alcohol than other coupling/emulsifying agents frequently used in the art. Particularly

preferred monofunctional amines include water-soluble organic amines such as monoethanolamine (MEA), 2-aminomethylpropanol (AMPS), and other n-alkyl substituted derivatives of these.

5 Preferred low molecular weight acids include $C_6 - C_{10}$ water-insoluble organic monoacids such as n-octanoic acid and the like. One preferred acid is that known under the trade designation "Emery" 658, available from Emery Chemical Company, which is a combination of n-
10 octanoic and n-decanoic acids.

Other compounds which may be used as couplers to increase the apparent water solubility of the phenyl substituted alkyl alcohol include glycol ethers such as ethylene glycol benzyl ether.

15 Couplers are present in ready-to-use compositions of the invention such that the amount of the coupler is always greater than or equal to about 3.0 times that required to fully solubilize the phenyl substituted alkyl alcohol. In the case where the coupler is the
20 combination of monoethanolamine and n-octanoic acid, the weight ratio of monoethanolamine to n-octanoic acid typically and preferably ranges from about 3:1 to about 1:1.

A determination of how much coupler to add so that
25 the amount of coupler is at or exceeds 3.0 times the minimum amount necessary to fully solubilize the phenyl substituted alkyl alcohol is easily performed by visual inspection of compositions containing various ratios of coupler to alcohol. Greater amounts of coupler may
30 decrease cleaning performance or coating removal efficiency of the compositions of the invention, and may be uneconomical.

Hydrocarbon Terpenes

One class of useful compositions within the present
35 invention (although not particularly preferred) are compositions comprising a phenyl substituted alkyl alcohol such as benzyl alcohol, a coupler such as the

reaction product of MEA with a combination of n-octanoic and n-decanoic acid, a hydrocarbon solvent such as a hydrocarbon terpene, and water. Hydrocarbon terpenes may afford the compositions within the invention grease
5 dissolving power, and may provide more pleasant odor.

Hydrocarbon terpenes useful in this class of compositions include the class of mono- or sesquiterpenes or mixtures thereof and can be acyclic or preferably monocyclic or bicyclic in structure. It is preferably
10 liquid at room temperature (25°C). Examples of acyclic hydrocarbon terpenes suitable for use herein include 2-methyl-6-methylene-2, 7-octadiene and 2,6-dimethyl-2,4,6-octadiene. Preferred monocyclic terpene hydrocarbons belong to the terpinene, terpinolene, and limonene
15 classes, for example the alpha, beta, and gamma terpinenes, the d and 2-limonenes and dipentene (essentially a limonene racemate). The limonenes occur naturally in certain fruit and vegetable essences. Preferred bicyclic terpene hydrocarbons include alpha and
20 beta-pinene. Especially preferred is the hydrocarbon terpene d-limonene. The hydrocarbon terpene may be added to the compositions of the invention at a level of about 0.5 to about 5.0 weight percent, more preferably from about 0.5 to 3.0 weight percent.

25 Surfactants and Optional Ingredients

Optional ingredients are those typically used in cleaning and floor maintenance products, such as surfactants, fragrances and dyes. A surfactant may be required when the user desires to quickly strip a coating
30 from a large surface. If a surfactant is used, the surfactant is preferably a low-foaming surfactant such as the low-foaming cationic fluorochemical surfactant known under the trade designation "FC-135" and the like, available from Minnesota Mining and Manufacturing
35 Company, St. Paul, MN ("3M").

Other surfactants such as sodium 1-octane sulfonate, sodium dodecylbenzene sulfonate, sodium tallowate, and

sodium xylene sulfonate are less efficient at coupling benzyl alcohol and other phenyl substituted alkyl alcohol solvents into solution than couplers derived from a water soluble organic amine and a water insoluble organic acid.

5 It may be advantageous to include a compatible thickening agent to render the viscosity of the compositions of the invention such that they may be applied to a vertical surface, e.g., a base board, and not run therefrom. If such running occurs, the residence
10 time of the composition with respect to the surface being cleaned should be reduced or the composition may run onto areas where it is not wanted. It has been found in practice with other compositions outside of the invention that colloidal magnesium aluminum silicate (sold under
15 the trade designation "Veegum" T) is a suitable thickening agent. This particular thickening agent is typically effective at a concentration of about 0.3 to about 0.6 percent by weight of total composition, but this concentration may vary with other thickening agents.

20 In use, the compositions of the invention may be sprayed as an aerosol or non-aerosol upon the surface to be cleaned, or simply poured thereon. Spraying can be accomplished by conventional mechanical spraying devices or by using an aerosol dispensing container with a
25 sufficient amount of suitable aerosol propellant such as a low boiling alkanes or mixtures thereof, such as a mixture isobutane and propane.

Method Of Removing Greasy Residues and/or Floor Coatings From Surfaces

30 The invention also pertains to a method of removing coatings from a surface, the method comprising:

- a) applying to the coating a composition comprising:
 - i) an effective amount of a phenyl
35 substituted alkyl alcohol having a water solubility of at least 0.1 weight percent;
 - ii) a coupler; and

iii) water,
wherein the amount of the coupler is at least
3.0 times the amount necessary to completely
solubilize the phenyl substituted alkyl
alcohol; and

- b) allowing the composition to contact the coating
for a time sufficient to at least partially
remove the coating.

A preferred method of removing coatings from a
surface comprises:

- a) applying to the coating a composition
comprising:

i) an effective amount of benzyl alcohol;
ii) a coupler comprising the salt of a water-
soluble organic amine and a water-
insoluble organic acid; and
iii) water,

wherein the amount of the coupler is at least
3.0 times the amount necessary to completely
solubilize the benzyl alcohol; and

- b) allowing the composition to contact the coating
for a time sufficient to at least partially
remove the coating.

In the methods of the invention, the compositions of
the invention may be applied with a mop, poured onto the
surface to be cleaned or stripped. The compositions may
also be applied by conventional floor maintenance
machines, or they may be sprayed as an aerosol or non-
aerosol upon the surface to be cleaned. Spraying can be
accomplished by conventional mechanical spraying devices
or by using an aerosol dispensing container with a
sufficient amount of suitable aerosol propellant such as
a low boiling alkanes or mixtures thereof, such as a
mixture isobutane and propane.

Further understanding of the compositions and
methods of the invention will be understood with

reference to a following examples wherein all parts and percentages are by weight unless otherwise specified.

EXAMPLES

Examples 1-7 and Comparativ Examples A-H

5 The concentrated compositions of Table A above were diluted with water at the dilutions indicated in Table 1 to formulate the compositions of Examples 1-7. The compositions of Comparative Examples A-H were formulated in accordance with the teaching of Examples 2, 3, 6, 7,
10 8, 9, 10, and 11, respectively, of U.S. Pat. No. 5,158,710, and are provided in Table 2 below.

 The compositions of Examples 1-7 and Comparative Examples A-H were tested to determine their proficiency in removing 10 coats of a commercially available urethane
15 sealant/acrylic finish from a composition vinyl tile strip, the sealant/finish available from Buckeye International, Inc., St. Louis, MO, under the trade designation "Citation."

 To make the coated strips used in the test, a
20 30.5 cm x 30.5 cm composition vinyl tile was coated with 10 coats of the sealant/finish and then cut into 2.5 cm x 15 cm strips. The coated tiles in each case were then put in an oven for 3 days at 49°C to allow the coatings to fully harden, and thus simulate aged and burnished
25 finish.

 The compositions of Examples 1-7 and Comparative Examples A-H were tested individually by immersing coated strips for 2.5 minutes in a 100 ml beaker filled with 90 ml of each composition so that the test strips did not
30 touch the inside or the bottom of the beaker. The composition in each case was agitated mildly with a magnetic stirrer set at 5 on a scale of 10. After 2.5 minutes, the tiles were removed and wiped lightly with a mohair cloth so that the final thickness (T_f) of the tile
35 plus residual coating could be measured. Tables 1 and 2 tabulate the results of the dip tests, where "% removed" was calculated by the equation: $100 \times (1 - T_f/T_i)$, where T_i

was the initial thickness of the coated tile (i.e., coating plus tile thickness).

It can be seen from the data in Tables 1 and 2 that the compositions of the invention (Examples 1-7) were more effective in the test than the Comparative Example compositions A-H. The compositions of Examples 1-3 (devoid of hydrocarbon terpene) were more effective in this test than the compositions of Examples 4-7.

Various modifications of the invention will be apparent to those skilled in the art. The examples and description are intended to support and enable the following claims, and are not intended to limit the scope thereof.

Table 1: Inventive Compositions 1-7

15	Concentrate From Table A	Dilution Ratio	Example Designation	Wt.% Solvent	% Removed
	Concentrate #1	1:15	4	2.49	88
		1:11	2	3.33	92
		1:10	3	3.63	90
20	Concentrate #2	1:8	4	4.43	87
		1:8	5	4.21	85
		1:10	6	3.45	67
		1:11	7	3.16	75

Table 2: Comparative Examples A-H

	Wt. % Ingrid.	Comparative Examples							
		A	B	C	D	E	F	G	H
5	Dowanol PPH	3.00	3.50	4.00	4.00	4.00	4.00	4.00	4.00
	MEA	1.8	0.5	0.05	1.5	0.9	1.5	1.5	1.5
	Sodium metasilicate	1.5	1.2	1.0	0	0.4	0.4	0.4	0.5
	Witco 1298	1.0	1.2	1.5	1.7	1.7	1.7	1.6	1.6
10	Witconate SXS (40%)	0	5.0	5.0	0	0	0	0	0
	DI water	92.7	88.6	87.8	92.3	92.6	91.9	92.1	92
	NaOH (50%)	0	0	0.2	0.5	0.4	0.5	0.4	0.4
15	% Removed	49	41	18	51	46	61	44	52

What is claimed is:

1. A composition suitable for stripping coatings from a surface, the composition characterized by:
 - 5 a) an effective amount of a phenyl substituted alkyl alcohol having a water solubility of at least 0.1 weight percent; and
 - b) a coupler,wherein the amount of the coupler is at least 3.0 times
10 the amount necessary to completely solubilize the phenyl substituted alkyl alcohol when the composition is diluted with water.
2. Composition in accordance with claim 1 further
15 characterized by said phenyl substituted alkyl alcohol being selected from the group consisting of benzyl alcohol, alpha-phenylethyl alcohol, beta-phenylethyl alcohol, and ethylene glycol benzyl ether.
- 20 3. Composition in accordance with claim 1 characterized by said coupler being the salt of a water-soluble organic amine and an acid comprising at least one water-insoluble organic acid.
- 25 4. Composition in accordance with claim 1 further characterized by including includes a hydrocarbon terpene.